



**NATROCHEM, INC.**  
P.O. BOX 1205  
SAVANNAH, GA 31402  
(912) 236-4464 FAX: (912) 236-1919  
[www.natrochem.com](http://www.natrochem.com)

## **DATA SHEET ATLAS BURGUNDY PITCH**

The term "pitch" usually connotes a residium of still bottoms type product. Rosin pitches contain no residium products. All are formulated from high quality, closely controlled raw materials and made to demanding specifications.

<b>TEST</b>	<b>TEST METHOD</b>	<b>SPECIFICATION</b>
Acid Number	QCL-8.2.4-2-4	130 - 150
Softening Point, Ball & Ring, °F	QCL-8.2.4-2-11	130 - 134

### **TYPICAL PROPERTIES**

Color, Gardner, 50%	7
Specific Gravity @ 60°F	1.03
Ash, %	0.1
Flash Point, COC, °F	370
Fire Point, COC, °F	435

Date of Revision: 1/4/04

The information in this data sheet is derived from the best available sources and is believed to be accurate. However, no guarantee is expressed or implied regarding the accuracy of these data or the use of this product, nor are any statements in this bulletin intended as recommendations to use our products in the infringement of any patents.

**OTHER NATROCHEM PRODUCTS**  
**DLC® - Galex® - Rosin Oils - Rosin Pitches - Tarene™**  
**Natro-Flex™ - Tar-Cel® - Natro-Cel®**