



NATROCHEM, INC.
P.O. BOX 1205
SAVANNAH, GA 31402
(912) 236-4464 FAX: (912) 236-1919
www.natrochem.com

DATA SHEET NATRO-REZ® 50

Natro-Rez 50 is a Coumarone-Indene resin and widely used in rubber, adhesive, paint, coating, and allied industries. Natro-Rez 50 is used primarily in dark rubber compounds as a tackifier and processing aid. Natro-Rez 50 is also available as a dry liquid concentrate, CI 50 DLC®-A at 74% actives.

| TEST | TEST METHOD | SPECIFICATION |
|--------------------------|--------------------|----------------------|
| Softening Point, B&R, °C | QCL-8.2.4-2-11 | 52 - 58 |
| Acid Number | QCL-8.2.4-2-4 | 1 Max. |
| Color, Coal Tar | QCL-8.2.4-2-18 | 18 Max. |

TYPICAL PROPERTIES

| | |
|--------------------------|-------|
| Softening Point, B&R, °C | 55 |
| Acid Number | 0, 75 |
| Color, Coal, Tar | 5 |
| Flash Point, COC °F | 365 |
| Fire Point, COC °F | 405 |
| Specific Gravity, @ 80°F | 1.09 |

Date of Revision: 08/20/03

The information in this data sheet is derived from the best available sources and is believed to be accurate. However, no guarantee is expressed or implied regarding the accuracy of these data or the use of this product, nor are any statements in this bulletin intended as recommendations to use our products in the infringement of any patents.

OTHER NATROCHEM PRODUCTS

**DLC® - Galex® - Rosin Oils - Rosin Pitches - Tarene™
Natro-Flex™ - Tar-Cel® - Natro-Cel®**